



TeifsShield

Alkali Resistant Primer



DESCRIPTION:

- 100 percent acrylic-based primer
- Improves the mechanical bond of the finish
- Reduces the chance of efflorescence which may result from the cement content of various bases
- Enhances the appearance and uniformity of the finish
- Water-vapor permeable. Does not create a vapor retarder
- Improves finish coverage

USES:

Exterior:

- Optional for:
 - Cementitious Base Coats:
for Swirl Textures Finishes
 - Full Synthetic Base Coats:
for dark color finishes
- Any surface suitable for Teifs finishes
Portland cement-based stucco



TeifsShield

Alkali Resistant Primer

COVERAGE:

Depending on the condition of the substrate and method of application, approximate coverages are:

- One Coat:
400 sq. ft. (37.2 m²) per gal. (3.78 L)

CONTAINER:

In plastic pails.

- Storage: Protect from sun and freezing at all times
-Do not stack more than 3 pails high
- Shelf Life: One year if properly stored.

DRYING TIME:

Approximately 1/2 to 4 hours depending on temperature, humidity, and substrate.

CLEANUP:

Water soluble prior to drying. Clean tools and containers with water before drying.

SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity

and treat. Any form-release agents or bond breakers must be removed.

- Uneven concrete or masonry can be leveled with either Teifs Base or Base DB Base Coat & Adhesive or other suitable, compatible product.
- For additional options, contact ParexLahabra Technical Services Department.

MIXING:

- Use clean equipment for mixing and preparation.
- Mix thoroughly. Only a small amount of clean potable water can be added.

APPLICATION:

- Read the entire label before using this product.
- Apply with a roller, brush or suitable spray equipment in a continuous coat.
- Teifs Shield must be completely dry before any Teifs finish coating is applied.
- When using Teifs Swirl Texture finishes, the primer should be tinted to the color of the finish coating.
- Keep container closed when not in use.

LIMITATIONS:

- Ambient and surface temperature must be 40° F (4° C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, unpainted and free from any residue which may affect the ability of the Teifs Shield to bond to the surface.
- Application in direct sunlight in hot weather may adversely affect aesthetics



Corporate Office
ParexLahabra, Inc.
4125 E. La Palma Avenue, Suite 250
Anaheim, CA 92807
(714) 778-2266
(866) 516-0061

Sales Office
Teifs
220 Burluson
San Antonio, TX 78202
(800) 358-4785

Plants
French Camp, CA
San Antonio, TX

