



DPR Swirl 1.5
DPR Swirl 3.0
DPR Choice .75
Teifs DPR Acrylic Finishes

DPR Sand 1.0
DPR Sand 1.5
DPR Smooth 0.5



DPR SWIRL 1.5



DPR SAND 1.0




DPR SWIRL 3.0



DPR SAND 1.5



DPR CHOICE .75



DPR SMOOTH 0.5

DESCRIPTION:

- 100 percent acrylic-based textured finish
- Dirt Pick-up Resistance (DPR) The surface of the finish hardens and does not soften again under heat. The non-tacky surface provides high resistance to accumulation of dirt, mold, and pollutants
- Integrally colored with high-quality pigments

USES:

Exterior or interior finish coat over:

- Teifs Exterior Insulation and Finish Systems
- Properly prepared masonry, stucco, and concrete surfaces
- Interior application over drywall, plaster, or properly prepared masonry or concrete

COMPOSITION:

- Binder base: 100 percent acrylic polymer with surface-hardening property
- Aggregate: Pure crushed marble, rust-free
- Water-based: VOC-compliant
- Pigment base: Titanium dioxide
- Color: Teifs standard colors or tinted to desired custom color



DPR Swirl 1.0 DPR Sand 1.0 DPR Swirl 3.0 DPR Sand 1.5 DPR Choice .75 DPR Smooth 0.5

DPR Acrylic Finishes

COVERAGE:

Depending on the condition of the substrate and method of application, approximate coverages are:

Swirl 1.5

Aggregate size: 1.5mm
120-135 sq. ft. (11-12.5 sq. m.) per pail

Swirl 3.0

Aggregate size: 3.0mm
70-95 sq. ft. (6.5-9 sq. m.) per pail

Choice .75

60-150 sq. ft. (6-14 sq. m.) per pail
Coverage varies due to texture.

Smooth 0.5

Aggregate size: 0.5mm
280-300 sq. ft. (26-28 sq. m.) per pail

Sand 1.0

Aggregate size: 1.0mm
150-165 sq. ft. (14-15 sq. m.) per pail

Sand 1.5

Aggregate size: 1.5mm
110-125 sq. ft. (10-11.5 sq. m.) per pail

CONTAINER:

- 65 lb (29.5kg) net weight in plastic pails.
- Storage: Protect from sun and freezing at all times
 - Do not stack pails more than 3 pails high
- Shelf Life: One year if properly stored

DRYING TIME:

24 hours under normal conditions. High humidity and low temperatures extend drying time.

CLEANUP:

Water-soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate. For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.

- Uneven concrete or masonry can be leveled with any TeifsBase Base Coat & Adhesive, or other suitable, compatible product.
 - For interior drywall, prepare as for painting.
 - Prime with TeifsPrime or Sanded Primer.
 - For application of TeifsPrime or Sanded Primer, refer to the Product Data Sheet.
 - For additional options, contact ParexLahabra Technical Services Department.
- #### MIXING:
- Use clean equipment for mixing and preparation.
 - Stir to obtain a homogeneous consistency using a heavy-duty 1/2-in. (13mm) drill with a rust free paddle at 400-500 rpm. Avoid air entrainment.
 - Add the amount of water needed to achieve finish texture. To avoid color variations, add the same amount of water to each pail of finish as indicated on product pail.
- #### APPLICATION:
- Read the entire label before using this product.
 - Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section.
 - Keep container closed when not in use.
 - Use a clean stainless steel trowel and apply a uniform coat the thickness of the largest aggregate size of the finish. For Teifs Choice .75 Finish, apply a coat slightly thicker than the largest aggregate size.
 - Texturing Choice .75 Finish: Follow the first application with a second application of Choice .75 Finish, using tools and techniques necessary to obtain the desired texture. The maximum thickness within the applied texture must not exceed 3/16 in. (5mm) with average thickness not more than 1/8 in. (3mm).
 - Texturing Swirl 1.0, Swirl 3.0, Sand 1.0, and Sand 1.5 Finishes: Use a clean plastic float or a stainless steel trowel. A plastic float will roll the large aggregates more than a stainless steel trowel. Continuously dry clean the plastic float or steel trowel while texturing. Use consistent pressure and motion to achieve the desired texture. See Teifs application guides.
- Texturing Smooth 0.5 Finish:
 - Optional: Level stucco brown coats with any TeifsBase Base Coat & Adhesive and let dry prior to finish application.
 - Smooth 0.5 Finish cannot generally be floated. Texture will be "as trowelled."
 - Smooth 0.5 Finish can be trowelled smooth to simulate the texture of limestone.
 - For smoothest application, apply in two tight coats. Allow first coat to dry enough that it will not be disturbed during application of the second coat. When second coat is partially dry, trowel to desired smoothness. Light, consistent misting with water during smoothing will increase smoothness. Variations in color tint and smoothness should be expected.
 - Spray application: To achieve consistent texture, spray application must use consistent motion, pressure, distance and spray angle. A job-site mock up for spray application is advised.

LIMITATIONS:

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Supplemental heat and protection from precipitation must be provided as needed.
- Use only on surfaces that are sound, clean, dry, unpainted, and free from any residue that might affect the ability of the finish to bond to the surface.
- Application in direct sunlight in hot weather may adversely affect aesthetics.



Corporate Office

ParexLahabra, Inc.
4125 E. La Palma Avenue,
Suite 250
Anaheim, CA 92807
(714) 778-2266
(866) 516-0061, Tech Line

Sales Office

Teifs
220 Burluson
San Antonio, TX 78202
(800) 358-4785

Plants

French Camp, CA
San Antonio, TX

