

WeatherSeal Trowel-On Specification

CSI SECTION 07 27 26

CSI SECTION 07 25 00 - Weather Barriers
CSI SECTION 07 27 26 - Fluid-Applied Membrane Air Barriers - Trowel On

PART 1 - GENERAL

1.1 SECTION INCLUDES

A. Manufacturer's requirements for the proper design, use, and installation of a 100% acrylic based, trowelon, fluid-applied water-resistive & air barrier membrane.

1.2 RELATED SECTIONS

- A. Section 03 30 00 Cast-in-Place Concrete
- B. Section 04 20 00 Unit Masonry
- C. Section 06 16 00 Sheathing
- D. Section 07 62 00 Sheet Metal Flashing and Trim
- E Section 07 90 00 Joint Protection
- F. Section 08 50 00 Windows
- G. Section 09 21 16 Gypsum Board Assemblies

1.3 REFERENCES

A.	ASTM B117	Test Method for Salt Spray (Fog) Testing
B.	ASTM C1135	Test Method for Determining Tensile Adhesion Properties of Structural Sealants
C.	ASTM D522	Standard Test Methods for Mandrel Bend Test of Attached Organic Coatings
D.	ASTM D2247	Practice for Testing Water Resistance of Coatings in 100 Percent Relative Humidity
E.	ASTM D4541	Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers
F.	ASTM E72	Test Methods of Conducting Strength Tests of Panels for Building Construction
G.	ASTM E84	Test Method for Surface Burning Characteristics of Building Materials
Н.	ASTM E96	Test Method for Water Vapor Transmission of Materials
I.	ASTM E283	Standard Test Method for Determining Rate of Air Leakage Through Exterior Windows, Curtain Walls, and Doors Under Specified Pressure Differences Across the Specimen
J.	ASTM E331	Test Method for Water Penetration by Uniform Static Air Pressure Difference
K.	ASTM E695	Method for Measuring Relative Resistance to Impact Loading
L.	ASTM E2134	Standard Test Method for Evaluating the Tensile-Adhesion Performance of an Exterior Insulation and Finish System (EIFS)
M.	ASTM E2178	Standard Test Method for Air Permeance of Building Materials
N.	ASTM E2485	Standard Test Method for Freeze/Thaw Resistance of Exterior Insulation and Finish Systems (EIFS) and Water Resistive Barrier Coatings

ASTM G155 Accelerated Weathering for Exposure of Non-metallic Materials and G153

1.4 SYSTEM DESCRIPTION

A. 100% acrylic based, trowelable water-resistive and air barrier membrane. Designed for use as an water-resistive and air barrier behind EIFS and other claddings. This product is installed over glass mat gypsum sheathing, cement board sheathing, CDX plywood, OSB*, concrete or CMU. *The system is qualified for application to OSB (oriented strand board) sheathing only in areas shown in the manufacturer's Acceptable Substrates and Areas of use Technical Bulletin.

B. Functional Criteria:

1. General:

- a. Flashing: Flashing must be continuous and watertight. Flashing must be designed and installed to prevent water infiltration behind EIFS and other claddings. Refer to Division 07 Flashing Section for specified flashing materials.
- b. The configuration of the water-resistive barrier, drainage plane and flashing and cladding assembly materials, must allow for the egress of incidental moisture.

2. Performance Requirements:

a. System to meet the performance and testing requirements of the International Code Council Acceptance Criteria AC 212 and ASTM E2570.

Material Test	Method	ICC and ASTM E2570 Criteria	Results
Accelerated Weathering	AC 212	25 Cycles followed by Hydrostatic Pressure Test: No water penetration on the plane of the exterior facing side of the substrate.	Pass: no water penetration
Air Infiltration	ASTM E2178	Calculated flow Rate at 75 Pa $(1.57 \text{ lb/ft}^2, 0.3 \text{ in H}_2\text{O}) = < 0.02 \text{ L/m}^2 \text{s} (< 0.004 \text{ cfm/ft}^2)$	<.00001 L/m²*s (0.00001 cfm/ft²) at 75 Pa (1.57 lb/ft², 0.3 in H₂O)
Air Leakage of Air Barrier Assemblies	ASTM E2357	Pass < 0.2 L/s·m² at 75 Pa) (< 0.04 cfm/ft² at 1.57 psf)	Pass
Air Leakage	ASTM E283	No Criteria	< 0.004 cfm/ft ²
Freeze-Thaw Resistance	ASTM E 2485	10 Cycles	Pass – No Deleterious Effects
Hydrostatic Pressure Test	AATCC 127 (Water Column)	Resist 21.6 in (55cm) water for 5 hours before and after aging	Pass: no water penetration
Nail Seal ability, Head of Water	ASTM D1970	No Criteria	Pass 5 inches of water
Racking	ASTM E72	Deflection at 1/8 in (3.2mm)	Pass -No cracking at field, joints or flashing connection
Restrained Environmental	ICC ES AC 212 / ASTM E2570	5 Cycles of wetting and drying	Pass -No cracking at field, joints or flashing connection
Structural Loading	ASTM E1233 Procedure A	10 Cycles @ 80% design load	Pass -No cracking at field, joints or flashing connection
Surface Burning Characteristics	ASTM E84	ICC and ASTM E2568 Flame Spread <25 Smoke Developed <450	Flame Spread =0 Smoke Developed =0
Tensile Bond Strength	ASTM E 2134/ ASTM C 297	Minimum 15 psi (104 kPa)	Pass all listed substrates, Stainless Steel, Color Coated Aluminum, Galvanized Metal, Copper, Aluminum, Rigid PVC, Flashing Membrane
Water Resistance	ASTM D 2247	14 Days	Pass – No Deleterious Effects.

Material Test	Method	ICC and ASTM E2570 Criteria	Results
Water Penetration	ASTM E331	2.86 psf (137 Pa) for 15 minutes	Pass 25.4 psf (1216 Pa) for 165 minutes
Water Penetration	ASTM E331	Tested after Structural Loading, Racking and Restrained Environmental Cycling at 2.86 psf (137 Pa) for 15 minutes	No Water Penetration
Water vapor transmission	ASTM E96 Procedure B	Vapor Permeable	7 perms
Weathering	ICC ES AC 212 / ASTM E2570	210 hours of UV Exposure, 25 cycles of accelerated weathering, 21.6 in (549mm) water column for 5 hours	Pass
Wind Driven Rain	F.S. TT-C-555B	No Criteria	Pass
VOC	EPA Reference Test Method 24	US EPA, South Coast AQMD and Greenseal Standard	10 g/L

1.5 SUBMITTALS

A. General: Submit Samples, Evaluation Reports and Certificates in accordance with Division 01 General Requirements Submittal Section.

1.6 QUALITY ASSURANCE

A. Qualifications:

- 1. All materials must be manufactured or sold by an active Manufacturer Member of ABAA and must be purchased from its authorized distributors.
- 2. Manufacturer: Must be an active member of ABAA.
- 3. Applicator:
 - a. Must have attended manufacturer's Educational Seminar.
 - b. Must possess a current manufacturer's certificate of education.
 - c. Must be experienced and competent in installation of plaster-like materials and liquid-applied weather-resistive membranes.

1.7 DELIVERY, STORAGE, AND HANDLING

- A. Delivery: Deliver water-resistive and air barrier materials in original packaging with manufacturer's identification.
- B. Storage: Store materials in a cool, dry location, out of sunlight, protected from weather and other harmful environment, and at a temperature above 40°F (4°C) and below 110°F (43°C) in accordance with manufacturer's instructions.

1.8 PROJECT / SITE CONDITIONS

- A. Installation Ambient Air Temperature: Minimum of 40°F (4°C) and rising, and remain so for 24 hours thereafter.
- B. Substrate Temperature: Do not apply water-resistive and air barrier materials to substrates whose temperature are below 40°F (4°C) or contain frost or ice.
- C. Inclement Weather: Do not apply water-resistive and air barrier materials during inclement weather, unless appropriate protection is employed.
- D. Water-resistive and air barrier materials must not be applied if ambient temperature exceeds 120°F (49°C) or falls below 40°F (4°C) within 24 hours of application. Protect base coat from uneven and excessive evaporation during hot, dry weather.

E. Prior to installation, the wall must be inspected for surface contamination, or other defects that may adversely affect the performance of the water-resistive and air barrier materials and must be free of residual moisture.

1.9 COORDINATION AND SCHEDULING:

A. Coordination: Coordinate water-resistive and air barrier coating materials installation with other construction operations.

1.10 WARRANTY

A. Warranty: Upon request, at completion of installation, provide manufacturer's Standard Limited Warranty.

PART 2 - PRODUCTS

2.1 MANUFACTURERS

- A. Manufacturer, Basis of Design: Parex USA, Inc., 4125 E. La Palma Ave., Suite 250, Anaheim, CA 92807 Contact: Architectural Sales (866.516.0061) or Technical Support (800.226.2424).
- B. Components: Obtain components from authorized distributors. No substitutions or additions of other materials are permitted without prior written permission from Parex USA for this project.

2.2 MATERIALS

- A. Water-Resistive Membrane & Air Barrier Coating:
 - 1. Parex USA WeatherSeal Trowel-On: 100% acrylic, non-cementitious, trowelable water-resistive and air barrier.
 - 2. Parex USA 396 Sheathing Tape: Non-woven synthetic fiber tape to reinforce the membrane at sheathing board joints, into rough openings and other terminations into dissimilar materials.
 - Flashing Membrane: Self sealing, polyester faced, rubberized asphalt membrane, 30 mils (0.76mm) thick.

2.3 RELATED MATERIALS AND ACCESSORIES

- A. Substrate Materials:
 - 1. Glass mat gypsum sheathing conforming to ASTM C1177.
 - Cement Fiber Sheathing conforming to ASTM C1186.
 - 3. Gypsum Sheathing: Minimum 1/2" (13mm) thick, core-treated, weather-resistant, exterior gypsum sheathing complying with ASTM C79.
 - 4. Plywood: Minimum 7/16" (8mm) thick exterior grade or PS 1, Exposure 1, minimum 7/16" thick, C veneer facing out, panels gapped 1/8 " at all edges.
 - 5. Oriented Strand Board (OSB): 7/16" 1/2" Wall-16 or Wall-24, approved by the APA, TECO, or PSI/PTL. Stamped as Exposure 1 or Exterior Sheathing with a PS2 or PRP-108 rating.
 - 6. Concrete Masonry Units (CMU): Non-painted (uncoated).
 - 7. Concrete (poured or pre-cast).
 - 8. Other Approved by water-resistive membrane and air barrier manufacturer in writing prior to the project.
- B. Flashing: Refer to Division 07 Flashing Section for flashing materials.

4 • Parex USA WeatherSeal Trowel-On Specification 07 27 26

PART 3 - EXECUTION

3.1 EXAMINATION

- A. Verify project site conditions under provisions of Section 01 00 00.
- B. Compliance: Comply with manufacturer's instructions for installation.
- C. Substrate Examination: Examine prior to water-resistive membrane and air barrier installation as follows:
 - 1. Substrate must be of a type approved by water-resistive membrane and air barrier manufacturer. Plywood and OSB substrates must be gapped 1/8 in (3.2mm) at all edges. Plywood and OSB substrates cut edges (non-factory edges) must be sealed with a water-resistive coating.
 - 2. Substrate must be examined for soundness, and other harmful conditions.
 - Substrate must be free of dust, dirt, laitance, efflorescence, and other harmful contaminants.
 - Substrate construction in accordance with substrate material manufacturer's specifications and applicable building codes.
 - 5. Maximum deflection of the substrate must be determine by the requirements of the exterior cladding.
- D. Flashing: Flashing must be installed prior to the water-resistive membrane & air barrier coating material and integrated with the wall field membrane to create positive drainage.
- E. Advise Contractor of discrepancies preventing proper installation of the water-resistive membrane & air barrier coating material. Do not proceed with the work until unsatisfactory conditions are corrected.

3.2 PREPARATION

- A. Protection: Protect surrounding material surfaces and areas during installation of system.
- B. Clean surfaces thoroughly prior to installation.
- C. Prepare surfaces using the methods recommended by the manufacturer for achieving the best result for the substrate under the project conditions.

3.3 MIXING

A. Mix water-resistive membrane & air barrier materials in accordance with manufacturer's instructions.

3.4 APPLICATION

- A. General: Installation shall conform to this specification and manufacturer's written instructions.
 - 1. Flash all rough openings with water-resistive membrane & air barrier coating material embedded with sheathing tape or 4 oz reinforcing mesh.
 - 2. Treat all sheathing joints, inside and outside corners and all exposed edges at terminations with water-resistive membrane & air barrier coating material and embed sheathing tape or 4 oz mesh.
 - 3. Embed 4 in. strips of either Sheathing Joint tape or 4 oz. mesh by applying water-resistive membrane and air barrier coating. Trowel-On per application instruction to 4 in. of each side of the joint and embed reinforcing fabric with a stainless steel trowel so that the color of the fabric is not visible.
 - 4. Apply water-resistive membrane & air barrier coating to the entire surface of the substrate with a stainless steel trowel to a minimum wet thickness of 1.6mm (1/16 inch).
 - 5. Ensure that the water-resistive membrane & air barrier coating laps onto all tracks and flashing to allow for any incidental moisture to be drained into the track/flashing.
 - Allow water-resistive membrane & air barrier coating to completely dry before proceeding with additional layers of the assembly.

Parex USA WeatherSeal Trowel-On Specification 07 27 26 • 5

3.5 CLEAN-UP

- A. Removal: Remove and legally dispose of water-resistive membrane & air barrier coating material from job site.
- B. Clean surfaces and work area of foreign materials resulting from material installation.

3.6 PROTECTION

- A. Provide protection of installed materials from water infiltration into or behind them.
- B. Provide protection of installed materials from dust, dirt, precipitation, freezing during installation, and continuous high humidity until fully cured and dry.
- C. Clean exposed surfaces using materials and methods recommended by the manufacturer of the material or product being cleaned. Remove and replace work that cannot be cleaned to the satisfaction of the Project Designer/Owner.

END OF SECTION

Rev. November 2011

Disclaimer: This guide specification is intended for use by a qualified designer. The guide specification is not intended to be used verbatim as an actual specification without appropriate modifications for the specific use intended. The guide specification must be integrated into and coordinated with the procedures of each design firm, and the requirements of a specific project. For additional assistance, contact Parex USA's Architectural Sales (866.516.0061) or Technical Support (800-224-2626).

NOTES

6 • Parex USA WeatherSeal Trowel-On Specification 07 27 26

PAREXUSA

WeatherSeal Trowel-On Specification

CSI SECTION 07 27 26



Corporate Office

Parex USA, Inc. 4125 E. La Palma Ave., Suite 250 Anaheim, CA 92807 (866) 516-0061 Tech Support: (800) 226-2424

Facilities

French Camp, CA North Hollywood, CA Riverside, CA Colorado Springs, CO Haines City, FL Duluth, GA Redan, GA Albuquerque, NM Allentown, PA San Antonio, TX

